

DECKFORM



PRODUCT

DECKFORM is a film faced plywood board manufactured with high-quality tropical wood selected veneers, with antiskid surface in one face and non-adherent in other. The product has 100% phenolic gluing.

ADVANTAGES

DECKFORM may be used in heavy-traffic areas due to its high mechanical resistance and material tightness. Antiskid.

USE

To be used as floor lining in high-traffic areas, such as mezzanine, truck body, scaffold, platform, and stage floors.

STRUCTURAL

A* face and counter-face plate, with C* core or higher. Waterproof PHENOLIC GLUING.

SURFACE

Coated with phenolic and antiskid film. DECKFORM is supplied with black coating and sealed edges.

WEIGHT

Film weight is 80/240 gr/m² (antiskid face) 40/120 gr/m² (smooth face).

MAINTENANCE

DECKFORM cleanup may be carried out with water or any other chemical.

➔ MEANCES

Lenght	Width	Thickness
2440mm	1220mm	12mm
2440mm	1220mm	15mm
2440mm	1220mm	16mm
2440mm	1220mm	18mm
2440mm	1220mm	19mm
2440mm	1220mm	21mm
2500mm	1250mm	12mm
2500mm	1250mm	15mm
2500mm	1250mm	18mm
2500mm	1250mm	21mm

✂ TOLERANCES

- Length = $l \pm 3\text{mm}$
- Width = $w \pm 2\text{mm}$
- Thickness: for $t \pm 0.5\text{mm}$

[] MECHANICAL RESISTANCE TESTS

Elasticity modulus	7,099.70 N/mm ²	7,278.40 N/mm ²
Rupture Strength	51.26 N/mm ²	57.01 N/mm ²
Proportionality Limit Strength	30.45 N/mm ²	32.24 N/mm ²
	Seco	Úmido
Shearing Strength	1.34 N/mm ²	1.03 N/mm ²

⌚ DURABILITY

Very high endurance is achieved when usage specifications are followed.